

## ABS (GF20% UL94 V-0)

	ASTMD955	-	%	0.2-0.5
	ISO 527	-	MPa	90
	ISO 178	-	MPa	140
	ISO 178	-	MPa	7100
	ISO 179/1eA	23	kJ/m <sup>2</sup>	6
	ASTMD256	23 / 6.4mm	J/m	60
	ISO 75	1.80MPa		97
	ASTMD648	1.82MPa/12.7mm		105
	ISO 306/B50	50N×50 /h		101
	-	-		95
	ISO 11359		× 1E-5/	3
	ISO 11359		× 1E-5/	8
	UL94	-	-	V-0/1.5mm 5VA/2.5mm
	ASTMD149	1.5mm	NW/m	22
	ASTMD495	3.0mm	sec(PLC)	-(7)
	ISO 62	-	%	0.3
	ISO 1183	-	g/cm <sup>3</sup>	1.33